Building & Joint Sealant

SealArm PS-P

(Formerly known as MYK Seal PSP)

Two Part Ploysulphide Sealant, Pouring Grade



TECHNICAL DATA SHEET

Product Description

SealArm PS-P is two packs Polysulphide based, tough flexible durable with strong adhesive sealant and is a pourable version, basically used for movement joints in concrete and pavements

Uses

- Sealing of expansion, contraction & construction joints in building structure such as Basements, subways, retaining walls, floors, external walls, roof terraces & ceilings especially structural expansion joint running through the ceiling.
- Sealing of dynamic structural cracks
- Sealing of water retaining structure joints such as Water tank, reservoir, dams, canals, and water treatment plant
- Sealing of joints in traffic areas such as Bridges, roads and car parking areas

Features and Benefits

- UV Resistant
- Good Weather ability
- · Flame and fuel resistant
- Excellent Flexibility and movement tolerance
- Good resistance to chemicals and hydrocarbons

Application Methodology

Step no. 1: Surface Preparation:

The surface should be clean, dry and free from Laitance and loose particles. Correct joint design should be followed. To use economic quantity of SealArm PS-P the Width: Depth ratio should be 2:1

Back Up Materials:

Insert compressible polyethylene, polyurethane, themocolfoam neoprene, polyethylene butyl rods as back-up material to control depth of sealant in the joint and to provide support for tooling of the sealant

Step no. 2: Priming:

Apply one coat of SealArm PS-P primer on porous surface with dry brush. Please ensure the primer should not apply on Bond Breaker. Primer to be applied only on both side of concrete surface. Allow the primer to dry for one hour and then apply the sealant as soon as possible and certainly within 8 Hours.

Bond Breaker:

Fix bond breaker tape such as self adhesive polyethylene tape on back-up material to avoid adhesion of sealant to the third surface.

Masking Tape:

Apply masking tape such as self-adhesive polyethylene, cellophane or cloth tape on both edges of the joint. It is used to improve the neatness of the finished seal by protecting the face edges of the joint. It may be removed immediately after Tooling of the sealant.

Step no. 3: Application Instructions:

Mixing:

Both parts of Polysulphide are Preweighed materials; by using paddle type mixer both the parts to be mixed till a smooth uniform Consistency mix is obtained.

Mixing time normally is around 8 to 10 minutes.

Application:

The joint surface must be clean dry & SealArm PS-P can be poured directly from the mixing container. Pour into the joint to the required level. It may be necessary after few minutes to top up the level of sealant after it has flowed into all joint irregularities. Finally strip of the masking tape that has been used.

Joint size suitability:

Joint width	Design Joint width
Minimum - 6 mm	Floor Joint : Expected
Maximum : 50 mm	movement X 4.33
Joint Depth	Width to depth ratio
	1:1 for floor joints
Porous surface : >12 mm	Movement factor
Maximum : 25 mm	Floor joint : 30%

Ver/7/Oct 2021 1 of 2

Building & Joint Sealant

SealArm PS-P

(Formerly known as MYK SEAL PS P)

Two Part Ploysulphide Sealant, Pouring Grade

Technical Data

Appearance	Base & Curing agent - Homogeneous smooth paste
	Base : Off white
Colour	Curing agent : Dark Brown
	Mixed-Standard grey
Mixed Density @ 25°C	1.55 to 1.65
Pot life @ 25°C	Minimum 30 minutes
Self leveling	Acceptable
Mixing Ratio by weight	Base : Curing agent 92 : 8
Hardness shore 'A' 25°C: After 7 days	Minimum 5
Curing time	7 days at 20°C
UV Resistance	Good
Weather ability	Good
Chemical resistance	Resistance to most alkalies & dilute acids, petrol, diesel or jet fuel and many solvent and vegetable oils.
Flammability	Flame and Fuel resistant as per BS specification
Service temperature	-40°C to +80°C

Specification

Meets BS - 5212: 1990 - Type FB (Fuel and Flame resistant) for cold-applied joint sealant system for rigid pavements,



TECHNICAL DATA SHEET

Consumption

Sealant Requires in Kgs W X D X L X Mixed Density 1000

W – Joint Width in MM
D – Sealant Depth in MM
L – Joint Length in Mtr
Mixed Density- It should be in qm/cc

Packaging

4 Kg Pack

Health & Safety

SealArm PS-P should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on t eyes have to be immediately washed with plenty of water and medical advice has to be taken.

Storage& Self Life

Store in cool dry place

12 months from date of manufacturing

Product Categories Available



Legal Note

The information, and, in particular, the recommendations relating to the application and end-use of MYK Arment products, are given in good faith based on MYK Arment current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with MYK Arment's recommendations. In practice, the difference in materials, substrates and actual site conditions are such that no warranty in respect of merchant ability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application & purpose. MYK Arment reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.

Ver/7/Oct 2021 2 of 2